

SMI, Inc.

12219 SW 131 Avenue
Miami, Florida 33186-6401 USA

Phone: (305) 971-7047
Fax: (305) 971-7048

Attn: Dirk Van Laer
Dend BVBA
Ambachtsstraat 46b
2390 Malle
BELGIUM

Date: 31-Jul-2000

SMI/REF: 00JUL298

Product: DEXTAIR (received 21-Jul-2000)

Dilution: As received and 10 percent

Page 1 of 3

BOEING D6-17487 REVISION N
Exterior and General Cleaners and Liquid Waxes,
Polishes and Polishing Compounds

Sandwich Corrosion Test	<u>Conforms</u>
Acrylic Crazing Test	<u>Conforms</u>
Paint Softening Test	<u>Conforms</u>
Hydrogen Embrittlement Test	<u>Conforms</u>

Respectfully submitted,



Patricia D. Viani, SMI, Inc.

Client: Dend BVBA
Product: **DEXTAIR**
Dilution: As received and 10 percent
Boeing D6-17487, Revision N

Date: 31-Jul-2000
SMI/REF: 00JUL298

Page 2 of 3

Sandwich Corrosion Test : Specimen preparation, testing, and interpretation shall be in accordance with ASTM F1110 using the following materials and with the following exceptions:

a. Reagents and materials exception:

- (1) Clad 7075-T6 aluminum alloy in accordance with QQ-A-250/13 (AMS 4049 or AMS-QQ-A-250/13 optional) (2024-T3 Alclad specimens are neither required nor optional.)
- (2) Bare 7075-T6 aluminum alloy in accordance with QQ-A-250/12 (AMS 4045 or AMS-Q-A-250/12 optional) anodized in accordance with BAC 5019 or MIL-A-8625, Type I. Anodize shall be sealed. (2024-T3 nonclad specimens are neither required nor optional).
- (3) Distilled or deionized water may be used in place of ASTM F1193, Type IV reagent grade water for control specimens.
- (4) The filter paper may be Whatman No. 5 or equivalent in place of Whatman GFA glass fiber paper.

b. Procedure exceptions:

- (1) The filter paper strips shall be 1 by 3 inches and shall be placed in the center of the sandwiched specimens.
- (2) Each sandwich specimen shall be held together with waterproof tape, with no more than 1 piece of tape (maximum width 0.75 inch) on each of two opposite edges.

c. Interpretation of result exceptions:

- (1) Leaching or lightening of the chromate sealed anodize coating shall not be cause for rejection.
- (2) Deposits or residues from the material being tested that are not products of corrosion of the test panel surface shall not be cause for rejection.
- (3) Special procedure for evaluation of fire extinguishing foams and liquids.
- (4) Panels shall have a rating of 1 (no more than 5 percent of the surface area shall be corroded) or better in accordance with ASTM F 1110. The preferred method of determining the corroded area is by using image analysis. Other means approved by the purchaser may be substituted.
- (5) Any corrosion in excess of that shown by the control group shall be cause for rejection.

	Bare 7075-T6 anodized per Mil-A-8625 Ty 1	Clad 7075-T6 Aluminum
CONC	1	1
Dilute	1	1
Control	1	1

Result Conforms

Client: Dend BVBA
Product: DEXTAIR
Dilution: As received and 10 percent
Boeing D6-17487, Revision N

Date: 31-Jul-2000
SMI/REF: 00JUL298

Page 3 of 3

Acrylic Crazeing Test:

The material being tested shall not craze, crack, or etch acrylic test specimens when tested in accordance with ASTM F 484 using Type C (stretched acrylic plastic in accordance with MIL-P-25690) stressed to an outer fiber stress of 4500 psi.

Type C (MIL-P-25690) As received: No crazing, cracking or etching.
Dilute: No crazing, cracking, or etching.

Result Conforms

Paint Softening Test Procedure:

- a. Testing shall be in accordance with ASTM F502 using the following coating systems.
- (1) BMS 10-79, Type II primer applied in accordance with BAC 5882 plus BMS 10-60, Type II enamel in accordance with BAC 5845.
 - (2) BMS 10-79, Type III primer applied in accordance with BAC 5882, plus BMS 10-100 coating in accordance with BAC 5795.
- b. Three specimens conforming to Section 13a.(1) and three specimens conforming to Section 13a(2) shall be used for each test condition.
- c. The material being tested shall not produce a decrease in film hardness greater than two pencils, or any discoloration or staining.

NOTE: Slight darkening of the BMS 10-100 surface is acceptable.

As received: Paint system 1: < 1 pencil hardness change after 24 hour post-exposure dry time.

Paint system 2: < 1 pencil hardness change after 24 hour post-exposure dry time; slight discoloration

Dilute: Paint system 1: < 1 pencil hardness change after 24 hour post-exposure dry time.

Paint system 2: < 1 pencil hardness change after 24 hour post-exposure dry time; slight discoloration

Result Conforms

Hydrogen Embrittlement Test:

Hydrogen Embrittlement testing shall be in accordance with ASTM F 519-93, using cadmium plated Type 1a, 1c, or 2a specimens. All requirements of ASTM F519-93 for specimens, preparation, testing, and reporting shall apply. Type 1a specimens shall meet the requirements of D6-4307.

Type 1C:

As received: No failures within 150 hours.

Dilute: No failures within 150 hours.

Result Conforms